


Exceeding The Limits To Always Get The Best

HIGH GLOSS

COLLECTIONS

800x1600 MM

CONNECTING THE VALUE OF SLAB



GLOSSY COLLECTION


CONTINUA+ LAMGEA SYSTEM Lamina


CONTINUA+ is the most efficient, highest-productivity technology for the accurately managed manufacture of porcelain slabs and tiles, also producible with traditional bodies. The slabs are, in fact, formed without using a traditional press or mould, ensuring maximum flexibility in terms of size and thickness.



CONTINUA+ seamlessly integrates the powder forming phase and subsequent digital decoration. The key strengths of this exclusive process are high quality texturing and unrivalled surface shine.

PRODUCT
Formats





The thicknesses are one of the most important elements characterizing.

9 mm is set aside for the most demanding product applications such as wall & floor.

GLOSSY
COLLECTION

APPLICATION Areas

AIRPORT

STAIRCASE

INDUSTRIES

GYMNASIUMS

HOTELS

CORRIDORS HALLS

SCHOOLS

SUPER MARKET

OFFICE

TECHNICAL Features

LIGHTWEIGHT

WATERPROOF

RESISTANT TO SCRATCHES

RESISTANT TO HIGH TEMPERATURES

EASY TO CLEAN

RESISTANT TO BENDING

100% NATURAL

RECYCLABLE

HYGIENIC

RESISTANT TO UV RAYS

GLOSSY COLLECTION

GLOSSY COLLECTION









AMANI CHOCO

Random Face 4

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM





BLUE PEARL

Random Face 2

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







COLONATA

Random Face 3

FINISH


HIGH GLOSS DARK

SIZE

800X1600 MM

THICKNESS

9 MM









EMPERADOR MARRON

Random Face 4

FINISH


HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM









EMPERADOR QUARTZ

Random Face 4

FINISH


HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM





FANTASY BLUE

Random Face 2

FINISH


HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







FOREST GREEN

Random Face 3

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







HARMONY ONYX

Random Face 3

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM









INDIC BROWN

Random Face 4

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







KENYA NERO GRANDE

Random Face 3

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM





MARQUINA BROWN

Random Face 2

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







OTTOMAN STEEL

Random Face 3

FINISH

HIGH GLOSS DARK

SIZE

800X1600 MM

THICKNESS

9 MM





ORIENT BROWN

Random Face 2

FINISH

HIGH GLOSS DARK


SIZE


800x1600 MM

THICKNESS


9 MM











ONICE PERSIA

Random Face 5

FINISH

HIGH GLOSS DARK

SIZE

800X1600 MM

THICKNESS

9 MM









PIETRA GREY

Random Face 4

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM









PIETRA GRIS

Random Face 4

FINISH


HIGH GLOSS DARK

SIZE

800X1600 MM

THICKNESS

9 MM









PULPISP MOSH

Random Face 4

FINISH


HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







ROSSO NATURAL

Random Face 3

FINISH


HIGH GLOSS DARK


SIZE

800x1600 MM

THICKNESS

9 MM









STONEX BLUE ONYX

Random Face 4

FINISH


HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM









TURKISH MINT ONYX

Random Face 4

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM









TURKISH BLUE ONYX

Random Face 4

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM







WALKER ZANGER

Random Face 3

FINISH

HIGH GLOSS DARK

SIZE

800x1600 MM

THICKNESS

9 MM

Cleaning & Maintenance

Our products are non porous (due to their high quality raw materials, stringent production parameters and state of the art technology), hence any dust or deposited waste cannot penetrate the surface.

For most cases only a damp cloth is sufficient for cleaning.

Regular cleaning highlights the aesthetic features of the surface and gives it exceptional shine.

For highly aggressive cleaning caused by some common food and substances follow the table below.

TYPE OF STAIN	CHEMICAL PRODUCT	EXAMPLE
Grease	Alkaline - Solvent	Detergent
Oil	Solvent	Ammonia, Backing Soda
Ink	Oxidant - Solvent	Alcohol, Liquid Bleach, Nail Paint Remover
Rust	Acid	Hydrochloric Acid, Vinegar, Red Harpic
Lime	Acid	Descaling Reagent, Hydro Chloric Acid
Cement	Acid	Hydro Chloric Acid
Wine	Alkaline	Ammonia, Liquid Bleach
Coffee	Alkaline - Solvent	Ammonia, Liquid Bleach
Rubber	Solvent	Alcohol, Thinner
Plaster	Acid	Hydro Chloric Acid
Candle Wax	Solvent	Alcohol, Thinner
Iodine	Oxidant	Liquid Bleach
Blood	Oxidant	Liquid Bleach
Ice Cream	Alkaline	Liquid Bleach

Note: It is recommended that any kind of stain needs to get clean immediately / as soon as possible.

Technical Specification

CHARACTERISTIC	STANDARD AS PER ISO13006:2018/ EN14411 Gr.BIa	MEAN VALUE	TEST METHOD
Regulatory Properties			
Deviation in Length and Width	± 0.30 % (±1.00mm)	± 0.10 %	ISO 10545-2
Deviation in Thickness	± 5.00 % (±0.50mm)	± 5.00 %	ISO 10545-2
Straightness in Side	± 0.30 % (±0.80mm)	± 0.10 %	ISO 10545-2
Rectangularity	± 0.30 % (±1.50mm)	± 0.10%	ISO 10545-2
Surface Flatness Central Curvature	± 0.40 % (±1.80mm)	± 0.50 %	ISO 10545-2
Surface Flatness Edge Curvature	± 0.40 % (±1.80mm)	± 0.50 %	ISO 10545-2
Surface Flatness Warpage	± 0.40 % (±1.80mm)	± 0.50 %	ISO 10545-2
Surface Quality	> 95% de ects free	> 95% de ects free	ISO 10545-2
Small Color Difference(for Plain Colour)	ΔE < 1.00	ΔE < 0.30	ISO 10545-16
Glossiness (Polished)	as per mfg.	Gloss Value> 90	Gloss Meter 60°
Glossiness (Matt)	as per mfg.	3 <Gloss Value<7	Gloss Meter 60°
Glossiness (Satin/Posh)	as per mfg.	7<Gloss Value<18	Gloss Meter 60°
Structural Properties			
Water absorption	≤ 0.50 %	≤ 0.060 %	ISO 10545-3
Bulk density	as per mfg.	Min. 2.28 g/cc	ISO 10545-3
Massive Mechanical Properties			
Modulus of rupture	Min. 35.0 N/mm²	Min. 42.0 N/mm²	ISO 10545-4
Breaking strength thickness <7.5	Min. 700.0 N	Min. 1000.0 N	ISO 10545-4
Breaking strength thickness ≥7.5	Min. 1300.0 N	Min. 1800.0 N	ISO 10545-4
Breaking strength thickness ≥(7.5mm)	Min. 1300.0 N	Min. 7500.0 N	ISO 10545-4
Surface Mechanical Properties			
MOH'S hardness #	as per mfg.	Glossy Min. 4*/ Posh Min. 6	BS EN 15771
Surface abrasion resistance #	as per mfg.	Glossy Min. 2/ Posh Min. 3	ISO 10545-7
Deep abrasion resistance #	Max. 175mm³	Max. 132mm³	ISO 10545-6
Thermal Hydrometric Properties			
Moisture expansion	Max. 0.06%(0.6mm/m)	Max. 0.02mm/m	ISO 10545-10
Thermal expansion(COE) at 100°C	as per mfg.	Max. 6.0 x 10⁻⁶	ISO 10545-8
Thermal shock resistance	Min. 10 Cycle	Min. 10 Cycle	ISO 10545-9
Impact resistance(COR) #	Min. 0.55	Min. 0.55	ISO 10545-5
Frost resistance	as per mfg.	Frost Proof	ISO 10545-12
Chemical Properties			
Resistance to staining glazed	Min. Class 3	Min. Class 4	ISO 10545-14
Resistance to household chemicals & swimming pool salts glazed	Min. Class GB	Min. Class GA	ISO 10545-13
Resistance to low concentrate acid and alkalis glazed	as per mfg.	Min. Class GLB**	ISO 10545-13
Resistance to high concentrate acid and alkalis glazed	as per mfg.	Min. Class GHB**	ISO 10545-13
Safety Properties			
Skid resistance(DCOF-DRY) ##	as per mfg.	Glossy P0(<[12]) / Posh ≥P[1]([12]-[2]4)	BS 7976-2
Slip resistance(DCOF)(R value) ##	as per mfg.	R9 to R[13]	DIN 51130
Fire resistance	as per mfg.	Fire Proof	N.A.

* With Nano polishe
** Except Hydrofluoric Acid & it's compound
# Tiles Intended for use on floor
As per customer requirement

Packing Details

PRODUCT	SIZE	THICKNESS	TILES / BOX	COVERAGE AREA / BOX	WEIGHT (Kg)
Highgloss Dark	800x1600mm	9mm	2pc	27.55 Sq ft	53 Kgs